

TITLE

High Temperature LCP for Wear Resistance

5

ABSTRACT OF THE DISCLOSURE

10 A high temperature liquid crystalline polyester (LCP) composition,
and articles made therefrom, that provides "good" to "excellent" wear
resistance at PVs (pressure x velocity) of at least 1.75 MPa-m/s (50,000
psi- fpm). The high temperature LCP being a matrix material containing
lubricating fillers and having an onset of melting temperature of at least
320°C.

15

S:\Patent Documents\Eng. Polymers\AD69xx\AD6929\AD6929 USPRV\AD6929 US NA Spec.doc